

Wall Thickness Tolerances for

Round Hot-Finished Tubing A519

	Wall Thickness Tolerance*,		
Wll Thickness Range	Percent Over and Under Nominal		
as Percent of	Outside Diameter	Outside Diameter	Outside Diameter
Outside Diameter	2.999 in. and	3.000 in. to 5.999	6.000 in. to 10.750
	smaller	in,	in.
Under 15	12.5	10.0	10.0
15 and Over	10.0	7.5	10.0

^{*} Wall Thickness tolerances may not be applicable to walls 0.199 in. and less; consult manufacturer for wall tolerances on such tube sizes.

O: 972.562.7997 F: 972.562.7991

E: sales@steelresource.com W: www.steelresource.com Mailing Address: 5100 Eldorado Parkway Suite 102 McKinney, Texas 75070